

Test Report

Innogaz Low Volume Tapping Tee LVT 4IPS x 1/2CTS
made of PE4710

Dated: Jun 27th 2016

Introduction

This report describes the tests administered for the release of Electrofusion LOW VOLUME TAPPING TEE Ø 4IPS X ½ CTS part of the Innogaz product range, manufactured by

Aliaxis Utilities & Industry Private Limited
Goa, India

Electrofusion Tapping Tees are composed of Eltex TUB 121 Cell Class PE445574C PE3408/4710 and suitable in Gas service line up to 145 psig or water service line up to 232 psig.

General

The fusion procedure and the qualification test were administered at the Test Laboratories of FRIATEC Aktiengesellschaft Technical Plastics Division, Mannheim, Germany with the pipes documented in the result tables.

All tests are based on ASTM F1055 "Standard Specification for Electrofusion Type Polyethylene Fittings for Outside Diameter Controlled Polyethylene Pipe and Tubing".

Fusion procedures based on the Assembly Instruction for Innogaz Electrofusion Fittings and were executed at operating temperatures between -20°F (-30°C) to 120°F (+50°C).

Subsequently, the test samples were subject to the following tests (ASTM F1055)

- Sustained Pressure Test	ASTM F 1055 9.2 (ASTM D2513/D1598) temperature 176 °F (80 °C) PE4710 HS 750psi >200h / 640psi >1000h PE2708 HS 670psi >200h / 580psi >1000h
- Minimum Hydraulic Burst Pressure Test	ASTM F 1055 9.1
- Impact Resistance Test	ASTM F 905
- Joint Crush Test (homogeneity of fusion)	ASTM F 1055 9.4

Proprietary Information

This report is the property of Aliaxis Utilities&Industry Pvt Ltd and FRIATEC Aktiengesellschaft and is loaned subject to the conditions that it or any information contained there in will not be used in any way detrimental to the interests of Aliaxis and that all copies will be returned immediately on demand.

Test Report

Innogaz Low Volume Tapping Tee LVT 4IPS x 1/2CTS
made of PE4710

Dated: Jun 27th 2016

Results

Technical Characteristics/ Marking

Marking: Innogaz Logo, Dimension, ASTM F1055 D2513, G, PE3408/4710, SDR11, Batch, fusion barcode

Conclusion

The requirements of the ASTM F1055 are fulfilled.

Dimensional Check

according to the drawing and ASTM F1055

The priority A characteristics (resistance, internal diameter etc.) are according to the drawing and ASTM D2513.

Conclusion

Test passed. The requirement of the ASTM F1055 are fulfilled

Sustained Pressure Test

according to ASTM F1055 9.2 (ASTM D1598)

Saddle / Outlet	Pipe	Assembly and fusion ambient temperature	Test temperature	Pressure [psi]	Time-to-Failure	Result
LVT 4IPS x 1/2 CTS	PE2406/2708	-20°F	176°F	145	205 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE2406/2708	-20°F	176°F	145	205 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE2406/2708	120°F	176°F	145	205 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE2406/2708	120°F	176°F	145	205 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE2406/2708	-20°F	176°F	136	1005 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE2406/2708	-20°F	176°F	136	1005 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE2406/2708	120°F	176°F	136	1005 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE2406/2708	120°F	176°F	136	1005 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE3408/4710	-20°F	176°F	156	205 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE3408/4710	-20°F	176°F	156	205 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE3408/4710	120°F	176°F	156	205 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE3408/4710	120°F	176°F	156	205 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE3408/4710	-20°F	176°F	151	1005 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE3408/4710	-20°F	176°F	151	1005 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE3408/4710	120°F	176°F	151	1005 h	no failure occurred
LVT 4IPS x 1/2 CTS	PE3408/4710	120°F	176°F	151	1005 h	no failure occurred

Conclusion

All samples met the requirements. No leakages recorded.

Test Report

Innogaz Low Volume Tapping Tee LVT 4IPS x 1/2CTS
made of PE4710

Dated: Jun 27th 2016

Minimum Hydraulic Burst Pressure Test

according to ASTM F 1055 9.1

Minimum time to failure 60-70s (desired value)

Saddle / Outlet	Pipe	Assembly and fusion ambient temperature	Test temperature	Time-to-Failure	Burst pressure	Result
LVT 4IPS x 1/2 CTS	PE2406/2708	-20 F	73 F	68 s	736 psi	ductile pipe failure
LVT 4IPS x 1/2 CTS	PE2406/2708	-20 F	73 F	68 s	736 psi	ductile pipe failure
LVT 4IPS x 1/2 CTS	PE2406/2708	120 F	73 F	68 s	723 psi	ductile pipe failure
LVT 4IPS x 1/2 CTS	PE2406/2708	120 F	73 F	68 s	723 psi	ductile pipe failure
LVT 4IPS x 1/2 CTS	PE3408/4710	-20 F	73 F	64 s	784 psi	ductile pipe failure
LVT 4IPS x 1/2 CTS	PE3408/4710	-20 F	73 F	64 s	784 psi	ductile pipe failure
LVT 4IPS x 1/2 CTS	PE3408/4710	120 F	73 F	65 s	778 psi	ductile pipe failure
LVT 4IPS x 1/2 CTS	PE3408/4710	120 F	73 F	65 s	778 psi	ductile pipe failure

Conclusion

All samples met the requirements. No leakages recorded

Impact Resistance Test

according to ASTM F 905

High 78.7 in.
Weight 11 lb

Saddle / Outlet	Pipe	Assembly and fusion ambient temperature	Test temperature	Result
LVT 4IPS x 1/2 CTS	PE2406/2708	-20F	70-77F	no break in the joint
LVT 4IPS x 1/2 CTS	PE2406/2708	-20F	70-77F	no break in the joint
LVT 4IPS x 1/2 CTS	PE2406/2708	120F	70-77F	no break in the joint
LVT 4IPS x 1/2 CTS	PE2406/2708	120F	70-77F	no break in the joint
LVT 4IPS x 1/2 CTS	PE3408/4710	-20F	70-77F	no break in the joint
LVT 4IPS x 1/2 CTS	PE3408/4710	-20F	70-77F	no break in the joint
LVT 4IPS x 1/2 CTS	PE3408/4710	120F	70-77F	no break in the joint
LVT 4IPS x 1/2 CTS	PE3408/4710	120F	70-77F	no break in the joint

Conclusion

All samples met the requirements. No leakages in the joint recorded

Test Report

Innogaz Low Volume Tapping Tee LVT 4IPS x 1/2CTS
made of PE4710

Dated: Jun 27th 2016

Joint Crush Test

according to ASTM F1055 9.4.1

Saddle / Outlet	Pipe	Assembly and fusion ambient temperature	Test temperature	Result
LVT 4IPS x 1/2 CTS	PE2406/2708	-20F	70-77F	Separation <15%
LVT 4IPS x 1/2 CTS	PE2406/2708	-20F	70-77F	Separation <15%
LVT 4IPS x 1/2 CTS	PE2406/2708	120F	70-77F	Separation <15%
LVT 4IPS x 1/2 CTS	PE2406/2708	120F	70-77F	Separation <15%
LVT 4IPS x 1/2 CTS	PE3408/4710	-20F	70-77F	Separation <15%
LVT 4IPS x 1/2 CTS	PE3408/4710	-20F	70-77F	Separation <15%
LVT 4IPS x 1/2 CTS	PE3408/4710	120F	70-77F	Separation <15%
LVT 4IPS x 1/2 CTS	PE3408/4710	120F	70-77F	Separation <15%

Conclusion

In all cases homogeneous fusion result were achieved. Only minor separations less then 15% of the total fusion zone could be seen.

Joint Crush Test

according to ASTM F1055 9.4.1

Saddle / Outlet	Pipe SDR17	Assembly and fusion ambient temperature	Test temperature	Result
LVT 4IPS x 1/2 CTS	PE80	-20F	70-77F	Separation <15%
LVT 4IPS x 1/2 CTS	PE80	-20F	70-77F	Separation <15%
LVT 4IPS x 1/2 CTS	PE80	120F	70-77F	Separation <15%
LVT 4IPS x 1/2 CTS	PE80	120F	70-77F	Separation <15%
LVT 4IPS x 1/2 CTS	PE100	-20F	70-77F	Separation <15%
LVT 4IPS x 1/2 CTS	PE100	-20F	70-77F	Separation <15%
LVT 4IPS x 1/2 CTS	PE100	120F	70-77F	Separation <15%
LVT 4IPS x 1/2 CTS	PE100	120F	70-77F	Separation <15%

Conclusion

In all cases homogeneous fusion result were achieved. Only minor separations less then 15% of the total fusion zone could be seen. No pipe deformation was occurred.